

ILFORD

GALERIE

SMOOTH GLOSS & PEARL PAPER IGSGP9 / IGSP9

ILFORD GALERIE SMOOTH PAPER is a premium microceramic RC paper designed to provide instant dry images with a real photo look and finish, from today's range of photo-dedicated desktop inkjet printers. ILFORD GALERIE SMOOTH PAPER is available in "Gloss" and "Pearl" finish.

FEATURES

- Smooth gloss/pearl surface
- Instant dry
- Superb photographic image quality and consistency
- Heavyweight look and feel of a real photograph
- Excellent compatibility with all high quality inkjet printers, especially those designed for photo output
- Good archival properties and fade resistance (see Note below)

PRINTER & INK COMPATIBILITY

Compatible with most photo-dedicated and photo-capable desktop printers and the corresponding vendor's inks.

AVAILABILITY

A4 (210x297mm) / U4 (8.5"x11")	25 sheets, 100 sheets – 250 sheets (USA only)
A3 (297x420mm) / U3 (11"x17")	25 sheets
A3+ (329x483mm) / U3+ (13"x19")	25 sheets

PHYSICAL PROPERTIES (TARGET VALUES)

	GLOSS	PEARL
Weight	280g/m ²	280g/m ²
Opacity	99%	99%
Caliper	275 micron	280 micron
Tint (Lab)	94.5, 1.0, -4.7	94.5, 1.0, -4.7
Gloss	22-28% (20°)	14-22% (60°)

NOTES

ILFORD GALERIE SMOOTH PAPER — like all unprotected nanoporous "instant dry" media. — is sensitive to environmental pollutants, an effect often referred to as "gas fading". "Gas fading" occurs with or without the media being exposed to light. Environmental humidity and air circulation play an important role in the "gas fading" issue. In a protected display, laminated or under glass, indoors and away from direct sunlight, life expectancy of up to 10 years can be expected with both the gloss and the pearl papers, depending on the ink used.

To archive this type of media, it should be stored in files and not open to well ventilated environments. In ventilated environments even in the dark "gas fading" can still occur.

The life expectancy of all inkjet media is influenced by humidity, light and the ink being used. At higher light levels or humidity, one should expect a shorter life expectancy than at low light level or humidity. Some inkjet printer inks also offer poor stability when compared with others. When storing and handling prints at the extremes of the environmental range (<10% r.h. and >70%), performance and permanence may be reduced.

Specifications subject to change without notice.